

RF-GQ-06 Resin

RF-GQ-06 Temporary Crown&Bridge Resin is a dental specific resin used for 3D printing. Printing temporary teeth, dental bridges, inlays, veneers, etc. During dental implantation or denture restoration, patients need to wear temporary crowns before wearing the official dental crowns.

Dental crowns protect the gums and pulp. The strong pressure resistance, impact resistance, and excellent edge adaptability of this material ensure the product's durability.



MATERIAL STATUS

Applications	Dental model
Appearance	Teeth yellow A1/A2
Form	Resin
Processing method	(surface exposure molding)LCD (surface exposure molding)DLP
Characteristics	High strength、 Good hardness High precision、 Easy to polish Wear-resistant

PHYSICAL PROPERTIES	Testing method	Typical value
Density	ASTM D792	1.05-1.15 g/cm ³
Viscosity	ASTM D445	1000-1400 mPa·s
Hardness	ASTM D2240	90D ShoreD

MECHANICAL PROPERTIES.

Tensile Strength	ASTM D638	75 MPa
Elongation at Break	ASTM D638	9 %
Flexural Strength	ASTM D790	110 MPa
Flexural Modulus	ASTM D790	2100 MPa

*The above parameters are for reference only. The performance of cured materials will be affected by factors such as equipment, environment, parameter settings, post-processing methods, and testing methods, which will cause great differences. Please contact us if necessary

Room 302, Building 3, Guole Science and Technology Park, 1 Lirong Road, Dalang
Subdistrict, Longhua District, Shenzhen, Guangdong, China

Tel: +86 755 27615363

Email:

info@rayformtech.com

www.rayformtech.com

PRINT PARAMETERS

Representative Machine	Exposure Time/s	Bottom Exposure Time/s	Bottom Layer Count	Lift Distance/mm	Lift Speed /mm · min ⁻¹	Retract Speed /mm · min ⁻¹
Phrozen sonic mini8K S	5	20	3	4+4	60+120	180+60
Elegoo saturn 3 Ultra	4	20	3	4+4	90+180	180+90
Crealty Halot-MAGE Pro	2	25	3	10	120+180	180+120
Anycubic Mono 4 Ultra	3	20	3	5+3	90+240	240+60
Elegoo saturn 4 Ultra	4	25	3	Default standard parameters of the device		
Anycubic M7 Pro	3	30	3	5+4	120+240	360+120

*Post-Processing Procedure and Note

- 1.The model can be cleaned using isopropyl alcohol in the ultrasonic cleaning machine, and try not to use high-frequency shock or force brushing the model to avoid damage to the surface details of the model.
- 2.Thoroughly blow the model dry with a hair dryer or the like;
3. It is recommended to remove the support for model with supports first, and then post-cure treatment. If you remove the supports after it's been post-cured , it will easily cause damage to the contact surface of the support point;
4. For some occasions where certain toughness is required, you can choose to cure with UV lamp for 5 minutes. The printed parts should be kept in a cool dry place.

*Safety Precautions

- 1.Eye Contact: Immediately flush with plenty of clean water (under eye lids) for at least 20 minutes. Hold eyelids apart to ensure flushing. Washing within one minute of contact is essential to achieve maximum effectiveness. Seek medical attention immediately.
- 2.Skin Contact:Remove contaminated clothing and rinse contact area thoroughly with soap and water.
- 3.3D resin is not approved for use with food, drink, or medical application on the human body
- 4.For additional information please see the Material Safety Data Sheet.

*Safety Precautions

Please store in a cool place below 25 degrees Celsius, away from direct sunlight. Ordinary visible light may cause the resin to polymerize and gel.